

TEST REPORT NO: 185993

Date: 14 March 2023

**PIERRE FREY SAS
47 RUE DES PETITS CHAMPS
75001 PARIS
FRANCE**


The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer	Not Specified
Description of article	I5549 BUDAPEST
Retailer style number	MULTI
Retailer Standard Number	NS
Order No./ Buyer	ADELINE JELAGO
Quality/Fibre Composition	NS
Date Sample Received/Test Started:	03 March 2023

Tests	Pass	Fail	Remarks
BS EN 1021-2 Ignition Source 1	X		

(please note our uncertainty of measurement has been taken into account when the above results were pass/failed)
(Any statement of conformity made in this report unless otherwise stated in the test specification(s) is in line with SGS United Kingdom (Leicester) Decision rule LEI-GEN-PROC-012).

Signature



M. Harrison Laboratory Manager

For and on behalf of
SGS United Kingdom Ltd

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer: **PIERRE FREY SAS** Test Report No: **185993**

Test Results

BS EN 1021-1 & 2:2014
Assessment of the ignitability of upholstered furniture
Part 1 – Ignition source smouldering cigarette / Part 2 – Ignition source match flame

Description of Test Sample: I5549 Budapest multi coloured fabric

Test Requested

The test specimen has been tested to BS EN 1021 – 1 & 2: 2014 Smouldering cigarette and match flame.

Pre – Treatment

The customer has stated that the supplied test specimen has not been chemically treated so therefore no water soaking procedure has been performed.

Conditioning

All materials to be tested and the cigarettes have been conditioned for at least 24 hours immediately before the tests in an atmosphere $23 \pm 2^{\circ}\text{C}$ and $50 \pm 5\%$ r.h.

Comments on Test Results

The test specimen meets the requirements of BS EN 1021-1 & 2: 2014 where the result for both tests has been stated as non-ignition.

Uncertainty of measurement:

Source 0	
Progressive Smouldering	+0 secs / -60 secs
Source 1	
Smouldering	+0 secs / -60 secs
Flaming	+0 secs / -2 secs

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer: **PIERRE FREY SAS** Test Report No: **185993**

Test Results

'The test results relate only to the ignitability of the combination of materials under particular conditions of test; they are not intended as a means of assessing the full fire hazard of the materials in use.'

Ignition source Smouldering Cigarette

	Criteria of ignition	Cigarette 1 Criteria Observed	Cigarette 2 Criteria Observed
Progressive smouldering ignition	Clause 3.1a	No	No
	Clause 3.1b	No	No
	Clause 3.1c	No	No
	Clause 3.1d	No	No
	Clause 3.1e	No	No
Flaming ignition	Occurrence of flames	No	No
	Ignition occurring	Non – Ignition	Non – Ignition

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer: **PIERRE FREY SAS** Test Report No: **185993**

Test Results

Ignition source Match Flame

	Criteria of Ignition	Match Flame 1 Criteria Observed	Match Flame 2 Criteria Observed
Progressive smouldering ignition	Clause 3.1a	No	No
	Clause 3.1b	No	No
	Clause 3.1c	No	No
	Clause 3.1d	No	No
	Clause 3.1e	No	No
Flaming ignition	Clause 3.2a	No	No
	Clause 3.2b	No	No
	Clause 3.2c	No	No
	Clause 3.2d	No	No
	Ignition occurring	Non – Ignition	Non – Ignition

The test specimen was tested over Combustion modified foam (CMHR) with a density of 35kg/m³.

Smouldering criteria of Ignition

- Clause 3.1a – Test assembly displays escalating combustion behaviour so that it is unsafe to continue
- Clause 3.1b – Test assembly that smoulders until it is largely consumed
- Clause 3.1c – Test assembly that smoulders to the extremities within the test duration
- Clause 3.1d – Test assembly that smoulders after one hour from application of the ignition source
- Clause 3.1e – Test assembly on final examination shows evidence of progressive smouldering

Flaming Ignition

- Clause 3.2a – Test assembly displays escalating combustion behaviour so that it is unsafe to continue
- Clause 3.2b – Test assembly burns until it is essentially consumed
- Clause 3.2c – Flame reaches the lower margin, either side or passed through the full thickness
- Clause 3.2d – Flaming continues for more than 120 seconds after removal of burner tube

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer:

PIERRE FREY SAS

Test Report No:

185993

Test Results



End of Report

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only