

**Pierre Frey sas
Mrs. Virginie Gendrot
47 rue des Petits Champs
75001 PARIS
Frankrijk**



Your notice of
28-10-2016

Your reference

Date
03-11-2016

Analysis Report 16.05784.02

Required tests :

**UK Furniture and Furnishings
(Fire) (Safety) regulations (1988)
No. 1324**

**UK Furniture and Furnishings
(Fire) (Safety) regulations (1988)
No. 1324**

**The Furniture and Furnishings (Fire) (Safety) regulations :
1988 No. 1324 - Schedule 4 part I – The cigarette test - BS 5852
part 1 (1979)**

**The Furniture and Furnishings (Fire) (Safety) regulations :
1988 No. 1324 - Schedule 5 part I – The match test - BS 5852
part 1 (1979)**

Identification number	Information given by the client	Date of receipt
T1621304	F3188 LOUISON - 41% WO, 39% WP, 17% CO, 3% PC	28-10-2016

Gina Créelle

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1621304 - F3188 LOUISON - 41% WO, 39% WP, 17% CO, 3% PC

The Furniture and Furnishings (Fire) (Safety) regulations : 1988 No. 1324 - Schedule 4 part I – The cigarette test - BS 5852 part 1 (1979)

Date of ending the test 03-11-2016
 Standard used UK Furniture and Furnishings (Fire) (Safety) regulations (1988) No. 1324

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Water soaking of the cover No
 Filling T 23140 (Recticel) * - non-fire retardant foam - ± 22 kg/m³

* The filling complies with the requirements as indicated in schedule 5 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoulders to extremities	no	no
Smoulders through thickness	no	no
Smoulders more than 1 hour	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Occurrence of flames	no	no
	non-ignition	non-ignition

Conclusion Non-ignition

Reference: T1621304 - F3188 LOUISON - 41% WO, 39% WP, 17% CO, 3% PC
The Furniture and Furnishings (Fire) (Safety) regulations : 1988 No. 1324 - Schedule 5 part I – The match test - BS 5852 part 1 (1979)

Date of ending the test 03-11-2016
 Standard used UK Furniture and Furnishings (Fire) (Safety) regulations (1988) No. 1324

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

Water soaking of the cover No
 Filling T 23140 (Recticel) * - non-fire retardant foam - ± 22 kg/m³

* The filling complies with the requirements as indicated in schedule 5 part 1 of the UK Furniture and Furnishings (Fire) (Safety) Regulations 1988

Flame application time (s) 20

	1	2
Smouldering criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Smoke/heat/glowing more than 15 min min	no	no
Final examination / active smouldering	no	no
Flaming criteria		
Unsafe escalating combustion	no	no
Test assembly consumed	no	no
Flaming > 120 s	no	no
Afterflame time (s)	1	1
	non-ignition	non-ignition

Conclusion Non-ignition