

Pierre Frey sas 47 rue des Petits Champs **75001 PARIS** France

Your notice of 01-06-2021

Your reference

Date 11-06-2021

Analysis Report 21.03618.16

Required tests :

EN 13773 (2003)

Sample id	Information given by the client	Date of receipt
T2112492	F3588 TITLIS	01-06-2021

freelle

Gina Créelle Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.





CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

GENT • Technologiepark 70 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 29 27 00 • fax +32 56 29 27 01 • info@vkc.be VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB



Reference: T2112492 - F3588 TITLIS

<u>Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the</u> <u>ignitability of vertically oriented specimens.</u>

Date of ending the test Standard used Product standard	04-06-2021 EN 1101 (1995) + A1 (2005) EN 13773 (2003)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Ignition	Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length		
Flame application	Cases of	Cases of
time (s)	ignition	non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated No ignition within 20 s



Width		
Flame application	Cases of	Cases of
time (s)	ignition	non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated No ignition within 20 s

Performed under accreditation in the fire lab under the responsibility of Mike De Vrieze

in f



Reference: T2112492 - F3588 TITLIS

<u>Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.</u>

Date of ending the test	10-06-2021
Standard used	EN 13772 (2011)
Product standard	EN 13773 (2003)

Deviation from the standard

\sim	1	•	
Con	ditic	ning	
0011	CFI UI C		

20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face A	Face A
Severance1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	155	140	140	135
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face A	Face A
Severance1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	180	125	170	170
Flaming debris	no	no	no	no

Classification in accordance with EN 13773

Class 1