



**Pierre Frey sas**  
**47 rue des Petits Champs**  
**75001 PARIS**  
**France**

**Your notice of**  
01-06-2021

**Your reference**

**Date**  
11-06-2021

## Analysis Report 21.03618.15

Required tests :

**EN 13773 (2003)**

Sample id	Information given by the client	Date of receipt
T2112491	F3586 HIDDEN PEAK	01-06-2021

**Gina Créelle**  
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

**Reference: T2112491 - F3586 HIDDEN PEAK**

**Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.**

Date of ending the test 04-06-2021  
Standard used EN 1101 (1995) + A1 (2005)  
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%


Ignition Bottom edge

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

**Length**

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
No ignition within 20 s



**Width**

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
 No ignition within 20 s

**Reference: T2112491 - F3586 HIDDEN PEAK**

**Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.**

Date of ending the test 10-06-2021  
 Standard used EN 13772 (2011)  
 Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

**Length**

	Face A	Face B	Face B	Face B
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	120	130	175	125
Flaming debris	no	no	no	no

**Width**

	Face A	Face B	Face A	Face A
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	205	135	155	140
Flaming debris	no	no	no	no

**Classification in accordance with EN 13773 Class 1**