



Date of Issue: 6/26/2023 Report Number: 23-002028

Revision Number:1

Date Order Received: 06/21/2023

For the Account of: Pierre Frey Inc.

1704 Chantilly Dr. NE

Suite 200

Atlanta, GA 30324

Client's Identification:

**16627 LEONA** 

## **CERTIFICATE OF TESTING**

**TEST PERFORMED:** NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E 1353-16 – Cover Fabric Test

## **TEST RESULTS**

Specimen	Char Length (in
1	0.6
2	0.5
3	0.5

**NOTES** 

**Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity

## **ACCEPTANCE CRITERIA**

- 1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
- 2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover fabric.
- 3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

CONCLUSION	Based on the above Results and Acceptance Criteria, the item tested is:	
	☑ Class I	
	☐ Class II	

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature Date Order Completed: 06/26/2023